

PIC-MSM-320 Snap-fit Miniature Magnet


Data

Housing Material	PA66, black	
Orientation	over housing length	
Remanence Br	mT	1190
Coercivity HcB	kA/m	828
Coercivity HcJ	kA/m	1512
Energy Product (BH) max.	kJ/m ³	275
Magnetic Moment M	x10 ⁻⁵ Vs cm	2.40
Operating Temperature max.	°C	85
Temperature Coefficient Tk(Br)	%/°C	-0.10

Nominal values unless otherwise specified

Dimensions

in mm



Customized types, other magnet materials and high temperature grades available.