

## PIC-M150604 Bonded Ring Magnet


### Data

<b>Material</b>	SmCo, bonded	
<b>Orientation</b>	12-pole axially	
<b>Remanence Br</b>	mT	600
<b>Coercivity HcB</b>	kA/m	410
<b>Coercivity HcJ</b>	kA/m	796
<b>Energy Product (BH) max.</b>	kJ/m <sup>3</sup>	60
<b>Magnetic Moment M</b>	x10 <sup>-5</sup> Vs cm	-
<b>Operating Temperature max.</b>	°C	100
<b>Temperature Coefficient Tk(Br)</b>	%/°C	-0.11
<b>Density</b>	g/cm <sup>3</sup>	5.6

Nominal values unless otherwise specified

### Dimensions

in mm



Customized types available.