COIN TYPE PAS CAPACITOR





REFLOW

FEATURES

High capacity / High reliability

PAS can store a large number of ions into its amorphous structure (doping), therefore PAS capacitor has much larger capacity than conventional electric double layer capacitor. In addition, PAS is extremely stable material and PAS capacitor shows excellent performance of cycle life and durability to overcharge and overdischarge.


RoHS / WEEE compliance

PAS capacitors are RoHS and WEEE compliant products and have no recycling and collection duty that is required in lithium ion battery's case.


APPLICATIONS

• Memory and RTC back-up power source used for cellular phone, PDA, digital camera, portable radio and so on.

ORDERING CODE




EXTERNAL DIMENSIONS



■ EXTERNAL DIMENSIONS, WEIGHT





Туре	φD(mm)	H(mm)	Weight(g)	
311	3.8 (0.150)	1.1 (0.043)	0.03	
409	4.8 (0.189)	0.9 (0.035)	0.05	
414	4.8 (0.189)	1.4 (0.055)	0.06	

*mm(inch), g

^{*} This catalog contains the typical specification only due to the limitation of space. When you consider the purchase of our products, please check our specification. For details of each product (characteristics graph, reliability information, precautions for use, and so on), see our Web site (http://www.ty-top.com/) or CD catalogs.

Part Number	Terminal Shape	LeadFree Reflowable	RoHS	Maximum Usable Voltage (V)	Nominal Capacity (µAh)	Nominal Capacitance (F)	Typical Internal Resistance (Ω)
PAS311HR	VA6R	0	0	3.3	10 ^{*1}	0.03	120
PAS409HR	VE5R	0	0	3.3	12 ⁻¹	0.035	80
DAC414LID	VA5R	0	0	3.3	22*1	0.07	00
PAS414HR	VE5R	0	0	3.3	22	0.07	80
PAS311SR	VA6R	0	0	2.6	11 ⁻²	0.035	70
PAS414SR	VE5R	0	0	2.5	20 ^{*3}	0.07	37

^{(*1) :} Capacity is measured from maximum usable voltage to 2.0V.

HR Type

■ FEATURES


- Reflowable with lead-free condition (Refer to Reliability Data for recommendable reflow pattern)
- Voltage can be set up freely below 3.3V


SPECIFICATIONS


Part Number	311HR 409HR		414HR			
1. Operating Temp. Range	-20~+60°C					
2. Max. Usable Voltage	3.3V					
3.Initial Capacitance (F)	Over 0.02	Over 0.022	Over 0.03			
4.Initial Capacity (µAh)	Over 6	Over 7	Over 10			
5. Initial Internal Resistance (Ω)	Under 500	Under 300	Under 250			
6. Max. Discharge Current (µA)	10	20	20			
7. Temperature Characteristics	Highest temperature (60°C) Capacity: Over 90% of initial spec.					
7. Temperature Offdracteristics	Lowest temperature (-20°C) Capacity: Over 50% of initial spec.					

ELECTRICAL CHARACTERISTICS

PAS414HR • Charging characteristics







SR Type

FEATURES

- Reflowable with lead-free condition (Refer to Reliability Data for recommendable reflow pattern)
- Voltage can be set up freely 2.5V for PAS414SR and 2.6V for PAS311SR

SPECIFICATIONS


Part Number	311SR	414SR			
1. Operating Temp. Range	−25~+70°C				
2. Max. Usable Voltage	2.6V	2.5V			
3.Initial Capacitance (F)	Over 0.025	Over 0.05			
4.Initial Capacity (µAh)	Over 8	Over 13			
5. Initial Internal Resistance (Ω)	Under 120	Under 120			
6. Max. Discharge Current (µA)	10	20			
7 Tama ayah wa Chayaatayistiaa	Highest temperature (70°C) Capacitance: Over 90% of initial sp				


7. Temperature Characteristics


Lowest temperature (-25°C)
Capacitance: Over 50% of initial spec.

ELECTRICAL CHARACTERISTICS

PAS414SR







^{(*2):} Capacity is measured from maximum usable voltage to 1.4V. (*3): Capacity is measured from maximum usable voltage to 1.5V.

^{*} This catalog contains the typical specification only due to the limitation of space. When you consider the purchase of our products, please check our specification. For details of each product (characteristics graph, reliability information, precautions for use, and so on), see our Web site (http://www.ty-top.com/) or CD catalogs.

1) Summary of Packaging Specifications


Item	Terminal Shape	Quantity per Reel	Products Direction ^(*)	Tape Width	Pitch	Reel Diameter	Emboss Shape
PAS311□□	VA6R	4000	_	16.0±0.3	8.0±0.1	330	Α
PAS409□□	VE5R	4000	_	16.0±0.3	8.0±0.1	330	В
PAS414	VA5R	4000	_	16.0±0.3	8.0±0.1	330	С
	VE5R	4000	_	16.0±0.3	8.0±0.1	330	С


(*) Indicate the polarity of terminal which is close to sprocket hole.

Unit : mm

②Taping Dimensions

Emboss Shape A






Unit: mm


Unit: mm

Unit: mm

Emboss Shape B



Emboss Shape C



③ Leader Section/Trailer Section


Leader section : Over 400mm

(Containing at least 44 vacant pockets of carrier tape sealed with top cover tape)

Trailer section :


(Over 5 vacant pockets of carrier tape sealed with top cover tape)

4 Reel Size



⑤ Peel Strength

0.1~0.7N under the condition of the figure below.



^{*} This catalog contains the typical specification only due to the limitation of space. When you consider the purchase of our products, please check our specification. For details of each product (characteristics graph, reliability information, precautions for use, and so on), see our Web site (http://www.ty-top.com/) or CD catalogs.


RELIABILITY DATA

lta	Specifi	cations	Total Constitutions Bounds		
Items	HR type SR type		Test Conditions, Remark		
1. Operating Temperature range	-20~+60°C	-25~+70°C			
2. Max. Usable Voltage	3.3V	2.5V (2.6V*)			
Resistance to Reflow Soldering Heat	Capacity/Capacitance: Within initial spec. Appearance: No noticeable abnormality		Conduct reflow soldering twice according to the reflow soldering test condition mentioned below. (Conduct the reflow in the condition of the voltage of 0.3V or lower.)		
4. Floating Charge Characteristics	Capacity/Capacitance: Over 70% of initial spec. Appearance: No noticeable abnormality		Apply a max.usage voltage to the capacitor for 500 hours at max. operating temp. and measure the floating charge characteristics after returning to normal temperature and humidity.		
5. Charge/Discharge Cycle Characteristics	Capacity/Capacitance: Over 50% of initial spec. Appearance: No noticeable abnormality		Measure the charge/discharge cycle characteristics after the 10000 cycles of charge/discharge at 25 \pm 5 $^{\circ}$ C with the charge/discharge cycle test condition for each part.		
6. Thermal Durability	Capacity/Capacitance: Over 80% of initial spec. Appearance: No noticeable abnormality		Leave the capacitor in an atmosphere of 85°C±2°C and -30 ± 2 °C consecutively for 96 hours each, and return to normal temperature and humidity.		
7. Humidity Durability	Capacity/Capacitance: Over 80% of initial spec. Appearance: No noticeable abnormality		Temperature : 40±2°C, Humidity : 90~95%RH Leave the capacitor for under the condition for 96hours then return to normal temperature and humidity.		
8. Vibration Durability	No exterior abnormality observed : initial spec. values retained		Apply a sine wave vibration of 1.5mm amplitude at frequency 10~55Hz, for 2ho per each direction (X,Y and Z), for 6 hours in total.		

(*): 2.6V for PAS311SR

Reflow Soldering Test Condition

Reflow profile with lead free condition



Cautions: Do not charge prior to reflow.

Set reflow condition within the range provided in "Specifications", which will be published separately.

Charge/Discharge Cycle Test Condition

Part Number	311HR	409HR	414HR	311SR	414SR
Charging/Discharging Resistance (Ω)	3000	3000	3000	150	150
Charging Voltage (V)	3.3	3.3	3.3	2.5	2.5
Charging Time (min.)	12	12	24	5	9
Discharging Time (min.)	3	3	6	0.5	1

PRECAUTIONS

1. Use under the maximum usable voltage.

If over maximum usable voltage is applied, it might cause abnormal current flow, which shorten lifetime, leakage and sometimes damage PAS capacitor.

2. Use under maximum operating temperature. Not only shorter life time but also leakage and damage will happen by increasing internal pressure if PAS capacitor use in over max operating temperature.

3 Limited life time

Lifetime of PAS capacitor is greatly affected by surrounding temperature. 10°C drop in temperature extend its expected lifetime approximately twice as much. Design a circuit under consideration of deterioration of electrical characteristics after long time usage, decreasing in capacitance and increasing in internal resis-

- 4. The electrical characteristics of capacitors vary with respect to temperature. The electrical characteristics of PAS capacitors temporarily vary with respect to temperature separately from secular change mentioned above. Design a circuit under consideration of temperature characteristics
- 5. PAS capacitor has polarity.

PAS capacitor has polarity. Please check the polarity before use. It will be damage if it is reverse charged.

6. Mind high ripple current or rapid charge / discharge.

In circuit with high ripple current or rapid charge / discharge, the lifetime of PAS capacitors might be shortened by self-heating.

7. Mind voltage drop when back-up.

When back-up (discharging) starts, voltage drop because of active current and internal resistance.

8. Series connection.

In case of using PAS capacitor in series connection, the voltage of each capacitor is not always equal and it may be occurred excessive voltage in a part of capacitor, which may lead to shortening lifetime and breakdown. Take a margin against a rated voltage or add a balancing resister.

9. Don't contact with wiring pattern during installing

If PAS capacitor contact with wiring pattern, it will be short circuit, and if there is wiring pattern underneath of PAS capacitor, short circuit would occur by damage of resist.

In case PAS capacitor is used in high humidity, alkaline or acid air, it may cause deteriorating of its performance and short circuit by corrosion of outer can or lead terminal. In addition, used in sudden temperature change or high humidity, it may cause deteriorating of its performance and electrolyte leak by dew condensation.

11. Don't apply shock and vibration or pressure.

PAS capacitor is sensitive to shock. Don't drop PAS capacitor and not apply strong pressure to a body, terminals and lead. Soldering part or lead terminal might be damaged if applying vibration, shock and stress such as pinch, tip, push and twist after installed.

12.Solderina

If next each item is not minded, it may cause deteriorating of its performance, leakage, shortening lifetime.

- Don't contact solder iron to a cell body.
- Don't solder over solder conditions in the spec. sheet.
- Don't charge/discharge before reflow.

*The use of the soldering iron is outside the guarantee of this product.

13. Mind cleaning condition when cleaning circuit-board after soldering. Cleaning may affect PAS capacitor. Consult us about cleaning conditions beforehand. Some cleaning conditions cause detrimental influence.

Keep following cautions for storage of PAS capacitor

- Don't store in the high temperature and the high humidity condition and a place where receiving direct sunlight. Storing PAS capacitor in the room condition of 10°C - 35°C and less than 65% relative humidity is recommended. Sudden temperature change or high humidity may cause deteriorating of its characteristics and Soldering.
- Don't store PAS capacitor near water, salt water or oil, and it the dew condensation, gasified oil or salinity filled place.
- Don't store PAS capacitor in the hazardous gas (hydrogen sulfide, sulfurous, chlorine, ammonia, bromine, methyl bromine and etc)
- Don't fumigate by halogen fumigant.
- Don't store PAS capacitor near acid or alkaline solvent.
- Don't store PAS capacitor in a place where exposed to ozone, ultraviolet or x-ray.

 • Don't store PAS capacitor in a place where vibration and shock might occur in.

15. Disposa

Dispose PAS capacitor in accordance with local and country rules and regulations.

16. Usage

PAS capacitor is developed on the assumption of the memory-backup & RTC for usage of information & communication equipment, home electronics, audio & visual equipment, office equipment and etc. Consult us about using high reliability and safety required products such as medical equipment, transportation equipment, industrial equipment, flight / space equipment and emergency equipment.

17. Other Notice

- Don't heat or throw PAS capacitor into fire.
- Don't short circuit.
- Don't solder directly to a cell body.
- Don' t open a body.
- Don't deform.
- Don't apply pressure.

^{*} This catalog contains the typical specification only due to the limitation of space. When you consider the purchase of our products, please check our specification. For details of each product (characteristics graph, reliability information, precautions for use, and so on), see our Web site (http://www.ty-top.com/) or CD catalogs.